

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.

THIS PAGE BLANK (USPTO)



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A41D 19/00, B32B 25/08	A1	(11) International Publication Number: WO 96/23428 (43) International Publication Date: 8 August 1996 (08.08.96)
(21) International Application Number: PCT/US96/01387 (22) International Filing Date: 26 January 1996 (26.01.96) (30) Priority Data: 08/382,611 2 February 1995 (02.02.95) US (71) Applicant: BAXTER INTERNATIONAL INC. [US/US]; One Baxter Parkway, Deerfield, IL 60015 (US). (72) Inventors: PLAMTHOTTAM, Sebastian, S.; 1496 Moonridge Court, Upland, CA 91784 (US). CALLOS, Bessie, E.; 3015 Maricotte Drive, Palmdale, CA 93550 (US). (74) Agents: STENZEL, Robert, A. et al.; One Baxter Parkway, Deerfield, IL 60015 (US).		(81) Designated States: JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: A MULTIPLE LAYERED ANTIMICROBIAL OR ANTIVIRAL GLOVE (57) Abstract The present invention involves an antiviral or antimicrobial surgical or examination glove. The glove comprises an elastomeric body in the shape of a hand having a inner surface and an outer surface. The inner surface comprises a hydrophilic/hydrogel polymer coating containing an antiviral or antimicrobial agent. The outer surface comprises a fluoroelastomer coating which blocks bacteria and viruses and is hydrophobic to bodily fluids.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

A MULTIPLE LAYERED ANTIMICROBIAL OR ANTIVIRAL GLOVE

FIELD OF THE INVENTION

This invention relates to a multiple layered glove having antimicrobial or antiviral properties. More particularly, the multiple layered glove has an outer coating of a fluoroelastomer and an inner hydrophilic coating containing an antimicrobial or antiviral agent.

BACKGROUND AND PRIOR ART

Polymers containing fluorine are known for their extraordinary toughness and resistance to heat, cold, erosion, abrasion, solvents, weathering and chemical attack. See U.S. Reissue Patent No. 24,856. For example, U.S. Patent No. 4,555,543 discloses a fluoroplastic resin dispersion modified by the addition of a fluoroelastomer latex yielding a fluid coating or casting composition.

U.S. Patent No. 4,214,321 discloses a glove that can be used to protect workers from a large number of chemicals and vapors. The glove has an outer layer of a fluorocarbon resin or a plasticized polyester resin which is flexible, solvent and abrasion resistant, a pin-hole free aluminum-foil middle layer and an inner heat sealable thermoplastic polymer material of polyethylene or polypropylene resin.

U.S. Patent No. 4,943,473 discloses fire and chemical resistant materials that can be used for gloves. These materials are produced by laminating a fluoropolymer containing film onto one or both sides of a flexible substrate. These materials retain their flexibility or suppleness and show enhanced resistance to chemical permeation and degradation.

U.S. Patent No. 5,194,335 discloses a coating or casting composition comprising a fluoroplastic resin

dispersion modified by the addition of a fluoroelastomer latex.

For decades, attempts have been made to improve the donability of surgeon's gloves. Surgeon's gloves
5 tend to have more critical requirements than examination gloves. Typically surgeon's like to don their gloves after "scrubbing up," without drying their hands. However, most surgeon's gloves are difficult to don with wet hands. Several attempts have been made to
10 improve the donability of surgeon's gloves.

One attempt to improve the donability of surgeon's gloves involved placing a slip coating on the inside surface of the glove. For example, U.S. Patent Nos. 3,286,011 and 3,411,982 disclose a process for making a
15 glove having a slip dip rubber-resin coating on the inside or outside surface of the glove. The slip dip rubber-resin coating comprises a rubber and resin latex. The resins disclosed as being suitable for use in the invention are: acrylic-type polymers and
20 copolymers, vinyl acetate polymers and copolymers, polyethylene, polyvinyl acetals, polyvinyl chloride or copolymers of vinyl chloride, styrene-acrylonitrile resins and high styrene-butadiene copolymer resins.

Other slip coatings are disclosed in U.S. Patent
25 Nos. 3,856,561, 3,919,442, 3,967,014 and 4,082,862. U.S. Patent No. 3,856,561 discloses a rubber article having a slip coating. The slip coating is a vinyl-chloride-alkyl acrylate copolymer or a vinylidene chloride-alkyl acrylate copolymer. In U.S. Patent No.
30 3,919,442, the slip coating comprises a first resin copolymer component consisting of a vinyl chloride-alkyl acrylate copolymer, a vinylidene chloride-alkyl acrylate copolymer and a vinyl acetate-alkyl acrylate copolymer and a second resin copolymer consisting of a
35 vinyl chloride-vinyl ester copolymer and a vinylidene chloride-vinyl ester copolymer. U.S. Patent No.

3,967,014, discloses a method for providing an essentially rubber free slip coating on a rubber surface by contacting a rubber surface with the slip coating disclosed in U.S. Patent No. 3,919,442 and
5 permitting said coating to form a resin slip coating on the rubber surface. U.S. Patent No. 4,082,862 discloses a process for producing rubber articles having a slip coating wherein a form is first coated with a release agent, then coated with a slip coating
10 composition deposited on the release agent and a rubber substrate deposited over the slip coating. The slip coating comprises of a non-elastomeric synthetic polymer component exhibiting an elongation of below about 20% and a coefficient of friction of up to about
15 0.20.

U.S. Patent 5,084,514 discloses a polymer latex for making gloves that has good donning and duffing characteristics. The glove is a terpolymer of carboxylated butadiene/acrylonitrile and methacrylic
20 acid.

In addition to the slip coatings described above, hydrophilic coatings have been used to coat the inside surface of surgeon's gloves to facilitate donning. Many hydrophilic monomers are known in the art such as
25 hydroxy alkyl acrylates, hydroxy alkyl methacrylates, vinyl lactams (eg. vinyl pyrrolidone), acrylamide and its derivatives, and ethylene oxide, just to name a few.

U.S. Patent No. 3,813,695 (the "Podell" patent)
30 describes a surgeon's glove in which the glove material is formed of a laminate consisting of an outer layer of a flexible material and an inner layer of hydrophilic plastic material (such as a hydrogel polymer), wherein the inner and outer layers are bonded together.

35 U.S. Patent No. 4,482,577 discloses a method of coating a vulcanized rubber article with a hydrophilic

polymer. The process involves dipping the rubber glove into a high concentration (95-100%) of sulfuric acid, washing the glove and then immersing the glove in a hydrophilic polymer.

5 U.S. Patent Nos. 4,499,154 and 4,575,476 describe a surgeon's glove in which the glove material is formed of a laminate comprising of an outer flexible layer and a lubricating polymer. Examples of a lubricating polymer disclosed are copolymers of 2-hydroxyethyl
10 methacrylate (HEMA) with methacrylic acid (MAA) or with 2-ethylhexyl acrylate (EHA) or with both methacrylic acid and 2-ethylhexyl acrylate. The hydrogel coating is further treated with a surfactant or long-chain
15 long-chain fatty amine enhances the lubricity of the innerlayer with respect to damp hands.

U.S. Patent No. 4,526,579 discloses a method of grafting a hydrophilic polymer onto the surface of a natural rubber article.

20 U.S. Patent No. 4,589,873 discloses a method for applying a hydrophilic polymer coating directly on to a substrate in order to provide a lubricous surface. Any polymeric substrate can be used. The substrate is contacted with a solution of the hydrophilic polymer in
25 a suitable solvent. Any applying solvent in which the hydrophilic polymer is soluble can be used. The solvent is then removed from the substrate leaving only the hydrophilic coating.

U.S. Patent No. 5,069,965 describes rubber and
30 vinyl articles having improved slip coatings. These rubber and vinyl articles have rubber-free extensible adherent slip coatings. One of the slip coatings disclosed is composed of the reaction product of about 55 to 80 mole % of a vinyl halide, about 15 to 32 mole
35 % of at least one copolymerizable ethylenically unsaturated hydrocarbon and about 3 to 10 mole % of at

least one copolymerizable monomer containing a carboxyl or amido group. The second adherent slip coating disclosed is the reaction product of about 76 to 94 mole % of a copolymerizable vinyl or vinylidene halide, about 8 to 11 mole % of acrylonitrile and about 2 to 12 mole % of at least one acrylic monomer. The second adherent coating provides an inner coating on gloves that facilitates wet donning.

Antimicrobial and antiviral gloves are well known in the art. It is especially necessary that surgeon's gloves be free of bacteria or other microorganisms during surgery. Prior to donning his gloves, a surgeon scrubs his hands with a strong bactericidal soap using a brush and/or a sponge. Then, using sterile techniques, he dons his gloves which have been presterilized in the package. If these steps are strictly adhered to, the surgeon's gloves do not convey bacteria to the wound or incision site. However, regardless of the amount of scrubbing the surgeon undertakes, bacteria remain embedded deep within the pores of his hands and skin. Unfortunately, these bacteria cannot be removed via scrubbing. Once the surgeon dons his gloves, the bacteria percolate out of the pores and reinfect the surgeon's hands. The bacteria do not present a hazard to the surgeon, but rather a hazard to the patient if the glove were to rip, tear or puncture during surgery.

In the same light, antiviral gloves are used by physicians, nurses and other healthcare professionals who may come in contact with viruses such as AIDS or Hepatitis B during routine medical examination.

U.S. Patent No. 4,584,192 discloses a film-forming composition containing an antimicrobial agent. The antimicrobial agent disclosed is a antimicrobial agent suitable for topical application such as chlorhexidine or a suitable derivative thereof. The film comprises

of three copolymerized monomers (A, B and C). Monomer A is a monomeric acrylic or methacrylic acid ester of an alkyl alcohol containing a single hydroxyl. Monomer B is a monomeric methacrylic acid ester of an alkyl alcohol containing a single hydroxyl. Monomer C is a N-vinyl lactam.

U.S. Patent No. 4,675,347 discloses a antimicrobial latex composition. The antimicrobial latex composition contains at least one cationic latex component and a cationic antimicrobial agent incorporated into the latex. The cationic latex component is either a cationic natural rubber latex or a cationic synthetic natural polymer.

U.S. Patent No. 4,853,978 discloses a antimicrobial multi-layered glove. The glove comprises an outer elastomeric coating and a inner coating. The inner coating has deposited on it a starch slurry containing antimicrobial agents thereby allowing the inner layer to slowly release the antimicrobial agent over time.

U.S. Patent 5,003,638 discloses a sterilized glove. Either the inside and/or outside layers of the glove contains an organic polymer film containing a antibacterial zeolite.

U.S. Patent 5,019,096 discloses a method for producing infection resistant materials. The infection resistant materials are prepared by: (1) preparing a coating vehicle by dissolving a matrix forming polymer (such as biomedical polyurethane, biomedical silicones, biodegradable polymers) into a solvent; (2) incorporating a antimicrobial agent such as a combination of chlorhexidine and its salts and silver and its salts; (3) coating a medical device with the coating composition; and (4) drying the coated medical device.

U.S. Patent Nos. 5,031,245 and 5,180,605 disclose

a natural rubber latex glove and a method for making such a glove containing an antimicrobial effective amount of a non-ionic, sparingly water soluble antimicrobial agent, such as 2,4,4'-trichloro-2'-hydroxy diphenyl ether. For example, the antimicrobial agent can be incorporated into a dispersion of aqueous natural rubber latex.

U.S. Patent No. 5,089,205 discloses a method for making a glove having antimicrobial properties. The method involves dipping a former into a gelled anionic natural latex to form an outer layer and then dipping the former into a second gelled anionic natural latex. The second anionic natural latex has incorporated into it a cationic antimicrobial agent. The cationic antimicrobial agent is stabilized in the anionic gelled latex through the use of an anionic surfactant. The glove is then cured and removed from the former.

U.S. Patent Nos. 5,128,168, 5,165,953, and 5,338,565 disclose a method for forming a latex membrane having a biocide barrier. In U.S. patent No. 5,128,168, a first coating of liquid latex is applied to a former. Next, a coating of a biocide which is effective as a coagulant is applied over the first latex coating. Finally, a second coating of liquid latex is applied over the biocide and the first latex coating. U.S. Patent No. 5,165,953 is almost identical to U.S. Patent 5,128,168 however, the biocide does not function as a coagulant for the second coating. U.S. Patent 5,338,565 is almost identical to U.S. Patent number 5,165,953, except that the first and second coatings are expanded to include polymeric latex, polymers dissolved in solvent and liquid polymers.

U.S. Patent 5,133,090 discloses an antimicrobial glove having an inner coating which contains an antiviral and lubricating agent. The antiviral agent is any suitable salts of chlorhexidine such as

chlorhexidine gluconate, chlorhexidine acetate and
chlorhexidine chloride. The lubricating agent
facilitates donning but does not significantly absorb
the antiviral agent. The inner coating is formulated
5 in such a manner that sufficient antiviral agent is
released within 10 minutes after exposure to a fluid
such as blood.

U.S. Patent No. 5,181,276 discloses an infection
resistant glove made from a molten blend of at least
10 one polymer and a compound having antioxidant,
plasticizer and antiviral activity. This compound has
a hydrophilic lipophilic balance of between 12 and 20.
An example of a suitable compound is nonoxynol-9.

U.S. Patent No. 5,236,703 discloses a polymeric
15 substrate manufactured from latex incorporating
povidone-iodine. The povidone-iodine is capable of
controlled release from the substrate. When contacted
with a polar solution such as blood or mucous
membranes, the povidone-iodine is released and
20 functions as a biologically active agent.

SUMMARY OF THE INVENTION

This invention involves a surgical or examination
glove. The glove comprises an elastomeric body in the
shape of a hand which is constructed from an
25 elastomeric polymer or copolymer such as natural rubber
latex, nitrile butadiene rubber, neoprene, butyl
rubber, and polyurethane.

The glove has a inner and outer surface. The
inner surface is coated with a hydrophilic/hydrogel
30 coating. The hydrophilic coating is a skin friendly
coating which has moisture absorbent properties. The
hydrophilic coating contains a antimicrobial or
antiviral agent which protects the wearer of the glove
from bacteria and viruses such as AIDS or Hepatitis.

35 The outer surface of the glove is coated with a
fluoroelastomer. The fluoroelastomer provides an

effective barrier towards viruses and functions as an effective barrier towards body fluids due to the hydrophobic nature of its surface. An example of a fluoroelastomer that can be used in this invention is
5 Tecnoflon TN latex available from Ausimont. Tecnoflon TN latex is a terpolymer of tetrafluoroethylene, hexa fluoropropylene and vinylidene fluoride.

DETAILED DESCRIPTION OF THE INVENTION

The present invention involves a surgical or
10 examination glove comprising an elastomeric body having an inner surface and an outer surface. The inner surface comprises a hydrophilic coating and the outer surface comprises a fluoroelastomer coating. The glove has plurality of superimposed layers which provide
15 improved cleanliness, barrier properties, 'skin friendliness' and comfort. In addition, the glove has very low particulates, ion extractable, non-volatile residues and surface contaminants. Further, the glove provides improved barrier protection against
20 microorganisms and viruses with improved comfort and skin friendliness in medical use.

The elastomeric body of the glove is made of a material that provides integrity and strength to the glove and eventually becomes the middle layer of the
25 glove between the two coatings. The body of the glove could be made out of any elastomeric polymer or copolymer such as natural rubber latex, nitrile butadiene rubber (NBR), neoprene (CR), butyl rubber (IIR), polyurethane and the like. If natural rubber
30 latex is used the latex can be any coagulatable natural or synthetic latex compound, coagulatable natural or synthetic rubber latexes or styrenic block copolymer dispersions known in the art. Conventional formulations for the preparation of latex are well
35 known in the art and one skilled in the art would be readily able to vary the formulations and conditions of

curing and the like to suit the particular latex being used as well as the final article desired. Precured, partially cured, or non-cured latex can be used.

Additionally, the latex may contain conventional
5 compounding ingredients commonly utilized. Specific examples are given in U.S. Patent 3,411,982, hereby incorporated by reference.

The inner surface of the glove, which is the skin contacting surface, comprises a hydrophilic/hydrogel
10 polymer coating. Hydrophilic/hydrogel polymers are preferred because they provide greater comfort and moisture absorption properties than other polymers. Examples of suitable hydrophilic coatings that can be used in this invention are disclosed in U.S. Patent
15 Nos. 4,436,887, 4,499,154, 5,575,476, 4,889,664, 4,411,922, 4,248,685 and 4,983,332, hereby incorporated by reference. For example, polymer compositions prepared from monomers comprising hydroxy alkyl acrylates, hydroxy alkyl methacrylates, vinyl lactams
20 (eg. vinyl pyrrolidone), acrylamide and its derivatives, ethylene oxide, and the like could be used. These monomers impart hydrophilic properties in the copolymer. Hydrophilic polymer blends prepared from polyvinyl alcohol, polyvinylpyrrolidone and the
25 like could also be used. The hydrophilic/hydrogel polymer may or may not be cross-linked.

The hydrophilic/hydrogel polymer contains a antimicrobial or antiviral agent. According to Dorland's Medical Dictionary, 27th edition (1985),
30 antimicrobial is defined as "(1) killing microorganisms or suppressing their multiplication or growth; and (2) an agent that kills microorganisms or suppresses their multiplication or growth." Antiviral is defined as
"(1) destroying viruses or suppressing their
35 replication; and (2) an agent that destroys viruses or suppresses their growth." Some antimicrobial agents can

be used as antiviral agents. Id. Examples of antimicrobial agents include: biguanides, including chlorhexidine and its salts, silver and its salts, polymyxin, tetracycline, aminoglycosides, rifampicin, bacitracin, neomycin, chloramphenicol, miconazole, quinolones, norfloxacin, nalidixic acid, perfloxacin, enoxacin and ciprofloxacin, pencillins, nonoxynol 9, fusidic acid, cephalosporins, and combinations thereof.

The antimicrobial agents would help protect against contamination from bacterial and other microbes.

Examples of antiviral agents include biguanide, such as chlorhexidine or a salts thereof, silver salts, such as AgSD, silver acetate, silver benzoate, silver carbonate, silver chloride, silver iodate, silver iodide, silver lactate, silver laurate, silver nitrate, silver oxide, silver palmitate, and silver salts of proteins, iodine, nonoxynol-9 and combinations thereof.

The antiviral agent would help protect against contamination from viruses such AIDS and Hepatitis B.

Certain additives such as emulsion silicones can also be added or coated on to the hydrophilic/hydrogel polymer used to enhance the donning and the release of the glove from the former. A silicone is generally defined as a compound that includes siloxane polymers which are based on a structure including alternate silicon and oxygen atoms, with organic groups attached to the silicon. Examples of suitable silicones that can be used include polydimethylsiloxane (PDMS), Dow Corning Silicone Emulsion 365, and the like.

The outer surface of the glove comprises a fluoroelastomer coating. Fluoroelastomers are any high polymer containing fluorine and can be homopolymers or copolymers. Fluoroelastomers exhibit elastomeric behavior or low flexural modulus. The term "fluoroelastomer" encompasses hydrogen containing fluoroelastomers as well as hydrogen-free

perfluoroelastomers. Examples of fluoroelastomers are homopolymers or copolymers of tetrafluoroethylene, hexafluoropropylene, pentafluoropropylene, chlorotrifluoroethylene, copolymers of vinylidene fluoride and hexafluoropropylene and tetrafluoroethylene and copolymers of vinylidene fluoride and chlorotrifluoroethylene.

For example, a fluoroelastomer coating based on Tecnoflon TN latex produced by Ausimont could be used as the outer coating. This coating would provide an effective barrier towards viruses and would function as an effective barrier towards bodily fluids due to the very hydrophobic nature of its surface. Other materials which would function in a similar way include polytetrafluoroethylene (PTFE)/natural rubber latex blend, Tecnoflon TN/PTFE blend, and the like.

The elastomeric nature of the fluoroelastomer coating is beneficial because it provides deformability better than rigid plastics as well as improved frictional characteristics, such as a higher coefficient of friction, especially when compared with chlorinated natural rubber gloves.

Because of the improved barrier properties of the fluoroelastomer coating, the overall thickness of the glove could be reduced, thereby improving the tactile sensitivity and fit. Another advantage is that particles will not stick and the coating will not shred during use. Finally, another advantage of the fluoroelastomer coating is that the coating will prevent the inner layers from oxidation and ozone attack.

The fluoroelastomer coating could be cured with a variety of curing agents. These include: aliphatic diamine derivatives, aromatic dihydroxy compounds with strong alkyl and aryl bases, or their suitable derivatives, basic metal oxides and hydroxides, and

peroxides with suitable co-agents, such as trimethylol propane, trimethacrylate, triallyl tri-mellitate. Typical cure systems for fluoroelastomers are discussed in an article by D.S. Ogunniyi and C. Hepburn in Rubber Processing and Applications 6 (1986) pages 3-9.

For example, a typical curing agent that could be used with the Tecnoflon latex coating includes triethylene tetramine (TETA), triethylene diamine (TEDA) and the like.

While the fluoroelastomer has been described as coating the outer surface of the glove, one skilled in the art would recognize that it can also be used to coat the inner surface of the glove as well.

Although the present invention has been described primarily in connection with gloves, it can also be used to form other skin-contacting articles such as catheters, ureters, sheets, condoms, etc.

In order that the present invention may be more fully understood, the following Examples are given by way of illustration.

EXAMPLE 1

Porcelain molds were washed and cleaned with soap and water to remove the smallest impurities such as minute specks of debris, oil, etc. because such debris can cause defects. The molds were rinsed with water and dried. After drying, the molds were heated and then dipped into a coagulant mixture that had been previously prepared by mixing:

	Methanol (100%)	:	76%	=
30	75.47 grams			
	Calcium Nitrate	:	16%	=
	16.06 grams			
	Calcium Carbonate	:	5%	=
	5.35 grams			
35	Lactic Acid (88%)	:	2%	=

2.87 grams

Triton X-10: 1% =0.27 grams

100%

5 100.00 grams

After dipping, the molds were air dried under the hood approximately 5-7 minutes to evaporate the methanol in the coagulant. The molds were then again dipped into the coagulant mixture which controls the latex thickness and helps release the glove from the mold later on. The mold was air dried once again under the hood for methanol evaporation, 5-7 minutes. Next, the molds were dipped into General Latex (Vultex 1-N-974) previously strained through a cloth sieve, gently and slowly to avoid bubbles and pinholes. When the mold emerged from the latex, an orchestrated waving motion was begun to distribute the latex evenly across the back to ensure a very thin filament coating. The mold is then leached in a water bath. The mold was then placed in an oven for 15 minutes to dry and set the latex. Temperature: 250°F (121°C). Once dried, the mold was allowed to cool down. The latex glove was then dipped into a previously prepared dispersion of 50 parts of Tecnoflon TN latex and 50 parts of deionized water, wherein a 10-15 ml of amine (triethylenetetramine or diethylenetriamine) was added to 1000 ml of the dispersion. Tecnoflon TN latex is a water based emulsion of 68% fluorine terpolymer fluoroelastomer containing a minimum of 70% solids. Again, an orchestrated waving motion was used to evenly distribute. The mold was placed in the oven to cure at a temperature of 250°F (121°C) for 15 minutes. After cooling, cold tap water was run through the glove while stripping it off the mold. The water layer on the glove prevents the coating from sticking to itself

during release. (Note: Triton X-100 was also used as an alternative to release the glove from the mold without sticking.) The fluoroelastomer coating was clear, smooth and exhibited a glassy coating. The
5 fluoroelastomer coating exhibited good anchorage to the latex and did not delaminate.

EXAMPLE 2

A preformed Latex glove was slipped in, flexed and stretched into a bisque finish glove mold. Solutions
10 of Teflon PTFE 30 and General Latex (Vultex 1-N-974) were prepared in disposable plastic beakers at different proportions such as:

- a) 600 ml General Latex + 400 ml Teflon 30
- b) 650 ml Teflon 30 + 350 ml General Latex
- 15 c) 750 ml Teflon 30 + 250 ml General Latex
- d) 800-900 ml Teflon 30 + 200-100 ml General

Latex

The glove mold was then dipped into the sample mixture slowly to avoid bubbles and pinholes, and
20 orchestrated in a waving motion for even distribution when it emerges from the mixture. Next, the mold was placed in an oven to cure, typically, at 120°C (250°F) for approximately 10 - 15 minutes. The mold was then allowed to cool down. The gloves were then inspected.
25 Glove (a) had a glossy, slightly sticky filament coating that was very strong and adhered well to the glove. The coating did not delaminate. Glove (b) had a glossy, slightly sticky filament coating that adhered well to the glove and was very strong. The coating did
30 not delaminate. Glove (c) had a glossy, slightly sticky coating that stuck to itself. The coating was very strong and did not delaminate. Glove (d) had a white, cracked coating. The coating exhibited poor

anchorage and delaminated.

EXAMPLE 3

The antimicrobial glove of this invention could be prepared as follows:

5 If the fluoroelastomer coating is to be on the outer surface after reversing, this can be accomplished by dipping the mold into a fluoroelastomer coating such as Tecnoflon TN latex. After withdrawal from the fluoroelastomer, the mold is dipped into a water or
10 alcohol based coagulant. After the dip in the coagulant, the mold is dipped into natural rubber latex. The length of time the former is immersed in the latex determines the thickness of the glove. The longer the dwell time period, the greater the wall
15 thickness of the article, and vice versa. The mold is removed from the latex with a coating of gelled latex adhering to it. The mold is placed in a water bath to leach out water soluble components such as proteins, electrolytes, etc. After the leach bath, a
20 hydrophilic/hydrogel polymer such as hydrophilic polyurethanes or acrylic such as copolymers of 2-hydroxyethyl methacrylate with methacrylic acid or 2-ethylhexyl acrylate or with both methacrylic acid and 2-ethylhexyl acrylate. The hydrophic/hydrogel polymer
25 contains an antimicrobial or antiviral agent. After the hydrophilic coating is applied the glove is cured or dried. Once dried, the glove can be stripped from the former. In order to enhance the release of the glove from the former, powder such as cornstarch or
30 calcium carbonate, or silicones, such as polydimethyl siloxane can be added.

Although the invention has been described primarily in connection with the special and preferred embodiments, it will be understood that it is capable
35 of modification without departing from the scope of the

invention. The following claims are intended to cover all variations, uses, or adaptations of the invention, following, in general, the principles thereof and including such departures from the present disclosure as come within known or customary practice in the field to which the invention pertains, or as are obvious to persons skilled in the field.

CLAIMS:

1. A surgical or examination glove comprising an elastomeric body in the shape of a hand having an inner surface and an outer surface, the inner surface
5 comprising a coating of a hydrophilic polymer containing an antimicrobial or antiviral agent and the outer surface comprising a coating of a fluoroelastomer.
2. The glove of claim 1 wherein the elastomeric body
10 is constructed from a polymer selected from the group consisting of: natural rubber latex, nitrile butadiene rubber, neoprene, butyl rubber, and polyurethane.
3. The glove of claim 1 wherein the antiviral agent is selected from the group consisting of: chlorhexidine
15 or salts thereof, silver salts, iodine, nonoxynol-9 and combinations thereof.
4. The glove of claim 1 wherein the antimicrobial agent is selected from the group consisting of: biguanides, silver and its salts, polymyxin,
20 tetracycline, aminoglycosides, rifampicin, bacitracin, neomycin, chloramphenicol, miconazole, quinolones, norfloxacin, nalidixic acid, perfloxacin, enoxacin, ciprofloxacin, penicillins, nonoxynol 9, fusidic acid, cephalosporins, and combinations thereof.
- 25 5. The glove of claim 1 wherein the fluoroelastomer is a homopolymer or copolymer selected from the group consisting of: tetrafluoroethylene, hexafluoropropylene, pentafluoropropylene, chlorotrifluoroethylene, copolymers of vinylidene
30 fluoride and hexafluoropropylene, and tetrafluoroethylene and copolymers of vinylidene fluoride and chlorotrifluoroethylene.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 96/01387

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 6 A41D19/00 B32B25/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B32B A41D A61B A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO,A,89 04647 (STILLMAN) 1 June 1989 see page 1, line 2 - page 2, line 15-20; claims 1,4,6,13,14,16; example 2 see page 3, line 18-28 - page 4, line 20 see page 6, line 7 - page 8, line 5 ---	1-5
Y	EP,A,0 328 421 (THE TRUSTEES OF COLUMBIA UNIVERSITY IN THE CITY OF NEW YORK) 16 August 1989 see page 3, line 15-25; claims 1,6,7,11,13,19,21,24,27 see page 4, line 10 - page 5, column 35-37; claim 32 see page 11, line 33-62 see page 13, line 29 - page 14, line 49; examples 2,3,6 see page 22, line 10-50; examples 11,17,20-23 --- -/-	1-5



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

12 June 1996

Date of mailing of the international search report

26 -06- 1996

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+ 31-70) 340-3016

Authorized officer

Derz, T

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 96/01387

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP,A,0 141 628 (UNITIKA LTD.) 15 May 1985 see page 4, line 4 - page 5, line 25; claim 1 see page 8, line 21 - page 10, line 15 see page 15, line 5-11 - page 18, line 7-11 see page 19, line 8-9 ---	1-5
Y	US,A,5 133 090 (MODAK ET AL.) 28 July 1992 cited in the application see column 2, line 30-66; claims 1,4,8,9 ---	2-4
Y	EP,A,0 300 814 (SURGIKOS INC.) 25 January 1989 see page 3, line 20-64; claims 1-3 ---	2-4
Y	WO,A,91 17047 (BRUNSWICK CORP.) 14 November 1991 see page 5, line 6-9; claims 1,4,5,12; figure 1 ---	1,2,5
Y	WO,A,90 14048 (BOARD OF REGENTS, THE UNIVERSITY OF TEXAS SYSTEM) 29 November 1990 see page 4, line 6-29; claims 1-4,6,11,15 ---	2-4
Y	WO,A,94 20574 (BAXTER INTERNATIONAL INC.) 15 September 1994 see page 1, line 4-29 - page 8, line 21-30; claims 1,2,4,9,10,13 ---	1-5
P,Y	WO,A,95 31102 (THE TRUSTEES OF COLUMBIA UNIVERSITY IN THE CITY OF NEW YORK) 23 November 1995 see claims 1,2,12 -----	1-4

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/01387

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-8904647	01-06-89	AU-B- 2727588	14-06-89
EP-A-328421	16-08-89	US-A- 5019096	28-05-91
		AU-B- 2989589	17-08-89
		JP-A- 2017071	22-01-90
		JP-B- 7090039	04-10-95
		US-A- 5133090	28-07-92
		AU-B- 636767	06-05-93
		AU-B- 7922991	03-10-91
EP-A-141628	15-05-85	JP-B- 6011813	16-02-94
		JP-A- 60094460	27-05-85
		JP-C- 1645557	28-02-92
		JP-B- 3010342	13-02-91
		JP-A- 60096258	29-05-85
		US-A- 4675347	23-06-87
US-A-5133090	28-07-92	US-A- 5019096	28-05-91
		AT-T- 120352	15-04-95
		AU-B- 635423	18-03-93
		AU-B- 7734091	23-01-92
		CA-A- 2043129	19-01-92
		DE-D- 69108469	04-05-95
		DE-T- 69108469	23-11-95
		EP-A- 0467869	22-01-92
		JP-A- 4241854	28-08-92
		JP-B- 6057220	03-08-94
		AU-B- 2989589	17-08-89
		EP-A,B 0328421	16-08-89
		JP-A- 2017071	22-01-90
		JP-B- 7090039	04-10-95
		AU-B- 636767	06-05-93
		AU-B- 7922991	03-10-91
EP-A-300814	25-01-89	US-A- 4853978	08-08-89
		AT-T- 113813	15-11-94
		AU-B- 604342	13-12-90
		AU-B- 1925188	27-01-89
		CA-A- 1302007	02-06-92
		DE-D- 3852067	15-12-94

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.

PCT/US 96/01387

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-300814		DE-T- 3852067	16-03-95
		ES-T- 2063037	01-01-95
		JP-A- 1043250	15-02-89
		JP-B- 3044527	08-07-91
WO-A-9117047	14-11-91	US-A- 5168010	01-12-92
		AU-B- 7890291	27-11-91
WO-A-9014048	29-11-90	AU-B- 5672790	18-12-90
		US-A- 5483697	16-01-96
		US-A- 5486322	23-01-96
		US-A- 5459879	24-10-95
WO-A-9420574	15-09-94	CA-A- 2134074	15-09-94
		EP-A- 0643743	22-03-95
		JP-T- 7506642	20-07-95
WO-A-9531102	23-11-95	US-A- 5487896	30-01-96
		AU-B- 2637095	05-12-95